06/14/2002 08:56

+19088745433

ARMADILLO ART USA

PAGE

14.Jun. 2002 11:21

EDUCATIONAL ART & CRAFT SUPPLIES

No.3655



SGS United Kingdom Ltd. Minerals Division

SGS House, 1 Johns Lane Tividale, Oldbury West Midlands B69 3HX Tel: (0121) 520 8454 Fax: (0121) 520 2438 Telex: 339118 SGSBHM

OASIS ART & CRAFT PRODUCTS LTD 17 Liste Avenue Kidderminster Worcestershire DY11 7DE



Date: 12th April 1999

Page: 1 of 6

Your Ref: Order No. 4351 Our File No: 10101/99

SAMPLE DESCRIPTION:

British Scraperboard

DETAILS OF SAMPLE:

These details are given on the following page.

TESTS REQUIRED:

The items were tested for compliance with the following

specifications.

B\$ 5665 : 1989 Part 1

Mechanical and Physical Regulrements

EN 71 : 1988 Part 1

Mechanical and Physical Requirements

BS 5666: 1994 Part 2 EN 71

: 1994 Part 2

Note BS 5665 and EN71 are Identical.

Flammability Flammability.

BS 5665 : 1995 Part 3

BS EN 71 -3: 1995

Migration of Certain Elements Migration of Certain Elements

TEST REBULTS

See Appendix.

CONCLUSION

In our opinion the submitted British Scraperboard samples listed on page 2 of this report satisfied the requirements of the specifications listed above.

ARMADILLU ARI USA

PAGE 62

14.Jun. 2002 11:22

EDUCATIONAL ART & CRAFT SUPPLIES

No.3655 P. 3/6



. _ ,0000193435

Sample Details:

Pack of Scraperboard, these being as follows:-

Sample Reference:	Sample Description:					
CSBB1	152x101 mm - box of 10 black sheets					
CSBB2	229x152 mm - box of 10 black sheets					
CSBB3	305x229 mm - box of 10 black sheets.					
CSBB4	502x305 mm - box of 10 black sheets	2007				
CSB86	610x502 mm - box of 10 black sheets	2001				
CSBW1	152x101 mm - box of 10 white sheets					
CSBW2	229x152 mm - box of 10 white sheets					
CSBW3	305x229 mm - box of 10 white sheets					
CSBW4	502x305 mm - box of 10 white sheets	1007				
CSBW5	810x502 mm - box of 10 white sheets	1001				

Page: 2 of 6

Date: 12th April 1999

Test Report No. 16163-4

ととといいいといいと

ARMADILLU ART USA

PAGE 03

14.Jun. 2002 11:22

EDUCATIONAL ART & CRAFT SUPPLIES

No.3655 P. 4/6



- 3.2.2. Requirements applicable to certain types of toys.
- 3.2.2.1 Small toys and detachable components: see 6.2

N/A

3.2.2.2 Non-detachable components: see 6.2

N/A

3.2.2.3 to 3.2.2.15 did not apply to these items.

5 <u>Packaging</u>

No plastic bags with an opening perimeter of greater than 380mm and a thickness of less than 0.038mm were seen.

PASS

6 Markings and Instructions for Use

These requirements for markings shall be made either on the toy itself, its packaging or a leaflet accompanying the toy.

8.1 Toys shall bear the name and address of the manufacturer or importer in a visible, easily legible and indelible form. Where these details are not affixed to the toy, the consumers attention shall be drawn to the advisability of keeping them.

These items were seen to satisfy these requirements.

6.2 Toys which might be dangerous for children under 38 months in age shall bear a warning, for example "not suitable for children under 36 months " together with a brief indication, which may also appear in the instructions for use of the specific risks calling for this restriction. This provision does not apply to toys which on account of their function, dimensions, characteristic properties or other cogent grounds, are manifestly unsuitable for children under 36 months.

These items were considered to be manifestly unsuitable for children under 36 months in age.

6.3 to 6.13 did not apply to these items.

Page: 4 of 8

Date: 12* April 1999

Test Report No. 16163-4

00/14/2002 00.05

+19088745433

ARMADILLO ART USA

PAGE 04

14.Jun. 2002 11:22

EDUCATIONAL ART & CRAFT SUPPLIES

No.3655 P. 5/6



British Standard 5665: 1994, EN71: 1994

Part 2: Flammability

Field of this application: these items were not listed.

N/A

4.1

General Requirements

No celluloid or material with the same nature in fire or flammable liquids and sollds were seen in these items.

PASS

4.2 to 4.5 did not apply to these items.

Bitish Standard 5665 : 1995, BS EN71 : 1996

Part 3 Migration of Certain Flaments

Principle: soluble elements are extracted from toy materials under the conditions which simulate the material remaining in contact the stomach acid for a period of time after swallowing. The concentrations of the soluble elements are determined quantitatively.

Selection of test portions: test portions are taken from accessible parts of a single toy, these test portions are only permitted to be more composed of more than one material or colour where physical separation precludes the formation of discrete specimens. Test portions where loss than 10mg of material are available are not tested.

7 Preparation of test portions – methods as described in the relevant sections of the specification were used.

The solutions obtained were analysed using an inductively Coupled Plasma Spectrophotometer calibrated with the appropriate standards.

Page: 5 of 6

Date: 12th April 1999

Test Report No. 16163-4

HISTHAULELU MIST OUR

14.Jun. 2002 11:22

EDUCATIONAL ART & CRAFT SUPPLIES

No.3655 P. 6/5



RESULTS:

All values are given as milligrams soluble element per kilogram of material, and have been re-calculated as described in Clause 4.2 of the specification.

Description of Sample	Sb	As	Ba	Cq	CT	Pb	Hg	Sé
Black Coating	< 5	<5	15	4 5	< 5	< 5	< 5	< 5
White Coating	< 5	<5	15	< 5	< 5	<5	< 5	<5
Cardboard Backing	< 5	<5	10	< 5	< 5_	< 5	< 5	< 5
Limit as specified	60	25	1000	75	60	90	60	500

All samples tested satisfied this part of the specification.

Tested By: S.A.Mole/S. Dhinsa

Test Date: 07/04/89 - 08/04/99

Authorised By;

Page: 6 of 6

Date: 12th April 1999

Test Report No. 18163-4